

High performance medium range super plasticizer for early, high strengths.

ألترا أدد أف 730

إضافة للخرسانة فائقة الجوده لزيادة الإجهاد .وتحسين قابلية التشغيل مع تأخير زمن الشك

Ultra - ADD F730 complies with ASTMC 494, Type A , F & Gand BS 5075 : part 3 : 1985.

Admixtures For Concrete

To promote high early and ultimate strengths by substantially reducing free water cement ratio whilst maintaining workability. To produce high workability concrete without loss of strength. To increase workability without reducing water: cement ratio, to produce high slump concrete mixes for piling works, etc. To facilitate production of high quality concrete of improved durability, density and water-tightness (less permeability). To use in concrete mixes containing micro silica.

إضافة خرسانية سائلة بنية اللون سريعة الإنتشار في الماء مناسبه لأجواء الحاره تحسن من قابلية التشغيل للخلطة الخرسانية وتأخير زمن الشك مع تقليل نسبة مياة الخلط وبالتالى زيادة الإجهادات المبكرة والنهائية للخرسانة.



High performance medium range super plasticizer for early, high strengths.



Uses

To promote high early and ultimate strengths by substantially reducing free water: cement ratio whilst maintaining workability. To produce high workability concrete without loss of strength. To increase workability without reducing water: cement ratio, to produce high slump concrete mixes for piling works, etc. To facilitate production of high quality concrete of improved durability, density and water-tightness (less permeability). To use in concrete mixes containing micro silica.

Advantages

Speeds construction by increased workability with easier and quicker placing and compaction, minimizing labour cost. Increases strength without increase in cement content or reduction in workability.

Advantageous in precast concrete production. Improves quality as lower water: cement ratio, and reduces shrinkage cracking potential. Improves durability bas denser and close - textured concrete surface without sand runs or voids. Eliminates largely bleeding and segregation. Chloride free. Safe in prestressed concrete and with sulphate-resisting cement or marine aggregates. Compatible with all Portland cements & most U.n.C. admixtures (to be added to mix Separately). Cohesion is increased by improved dispersion of cement particles, despite the fluid nature of collapsed slump concrete. Improves resistance to attack by aggressive agents.

Description

Ultra - ADD F730 is a brown liquid based on a blend of specially selected organic polymers, instantly dispersing in water. When added to the concrete mix, **Ultra - ADD F730** normally tend to agglomerate, to disperse and hence expose a larger surface area to the hydration processes. It may be used to produce high workability concrete or to increase strength by allowing substantial reduction in water content.

Specification compliance

Ultra - ADD F730 complies with ASTMC 494, Type A, F & Gand BS 5075: part 3: 1985.

Technical support

U.n.C. provides a technical service for on-site assistance and guidance on evaluation trials.

Properties (@ 25°C)

according to ASTM C494& Egyptian code

Appearance	Brown liquid	
Specific gravity	1.14 ± 0.04	
Solid content	32% ± 3%	
Ash content	13% ± 3%	
PH	6:10	
Chloride content	≤ 0.2	
Retarding setting time	170 min ± 20 min at normal dosage	
Air entrainment	Less than 2% according to dosage	



High performance medium range super plasticizer for early, high strengths.



Instructions for use

Dosage

The range is given as a guide:

	Dosage / 100 Kg cement
For increased strength	0.75 - 1.75
with water reduction	litres
For Increased	0.50 - 1.00
workability	litres
For concrete containing	1.50 - 2.50
micro silica / silica fume	litres

Mixing & Dispensing

A 'pump' mix design is required to produce a high workability concrete without risk of bleeding or segregation of aggregates, (Consult U.n.C. For mix design, and if cement content is outside the range 250 to 450 Kg / m³ or if the temperature is above 40 °C). The correct quantity of Ultra - ADD F730 should be added to the mixer simultaneously with mixing water,.

Curing

Normal curing methods such as water spray, wet hessian or a curing membrane of the Ultra - Cure type should be used.

Cleaning

Spillage of Ultra - ADD F730 can result in an increased level of retardation. The ultimate strength of the concrete will not be impaired and will generally be increased.

Storage

Ultra - ADD F730 has a minimum shelf life of 12 months provided the temperature is kept with in the range 2°C to 50°C. If this temperature is exceeded in any respect advice should be sought from the supplier.

Packaging

Ultra - ADD F730 is supplied in 210 litre drums, and also in tanker loads.



High performance medium range super plasticizer for early, high strengths.



Health and safety

Ultra - ADD F730 is non-toxic. Wash any splashes to the skin immediately with water. Splashes to the eyes should be washed immediately and medical advice sought.

Fire

Ultra - ADD F731 is non-flammable.













Quality You Can Trust

Aboraewash - Industrial Area Cairo - Alex. Road Km. 26 Adel Wali St. Land No. 91

Tel.:0100 931 8094 - 0100 044 9257

Email:sales@ultrachem-eg.com website: www.ultrachem-eg.com





النشرة الفنية

ألترا أدد أف 730

إضافة للخرسانة فائقة الجوده لزيادة الإجهاد وتحسين قابلية التشغيل مع تأخير زمن الشك.

وصف المنتج

إضافة خرسـانية سـائلة بـنية اللون سـريعة الإنتشـار في الماء مناسبـه لأجواء الحــاره تحســن من قابــلية التشــغيل للخلطة الخرســانية وتأخير زمن الشــك مع تقــليل نسبــة مياة الخلط وبــالتالـي زيادة الإجهادات المبكرة والنهائية للخرسانة.

- الإستعمالات تستعمل مع جميع أنواع الأسمنت عندما تكون الحاجة لإنتاج خرسانة ذات مقاومة مبـكرة ونهائية عالية ومناسبـــه لأعمال الإنشــــاءات عالية الجودة وذات إجهادات عالية وخالية من العيوب.
 - إنتاج خرســــــانة ذات قابـــــــلية تشــــــغيل عالية دون فقــــــــدان القـــــــوة.
 - تستعمل عند الحاجة لإنتاج خرسانة عالية الكفاءة في ظروف المناخ والتشغيل الصعبة.
 - مناسبــه للاســتخدام مع الخلطات الخرســانية التي تحــتوي على الميكرو ســيليكا.

المميزات

- يحســـن قابـــلية تشــــغيل الخرســــانة والمونه دون الزيادة في مياه الخلط.
- يؤخر زمن شك الخرسانة دون التقليل من قابلية التشغيل مما يساعد على نقل الخرسانة لمسافات أطول.
 - يحســن المتانه ومقـــاومه الماء ويحســن من الشـــكل النهائي للخرســـانة.
 - يقـــلل من مياة الخلط أكثر من% 20 مما يزيد من قـــوة الأنضغاط للخرســــانة.
 - يحســــــن قابـــــــلية التشـــــغيل, وتســــهيل صب ودمك الخرســــــانة.
 - يقلل ظاهرة نضح الخرسانة ويمنع إنفصال مكونات الخرسانة وكذلك التعشيش.
- يوفر في كمية الأســمنت حـــيث يزيد القـــوه دون الحـــاجه لكميات أســـمنت اضافيه وذلك دون التأثير على مقاومة الخرسانة.
 - خالى من الكلوريدات مما يجعلة أمن في الإستعمال في الخرسانة المسلحـة.

السانات الفنية

(عند 25 درجة مئوية)

المظهر	: سائل بني اللون
محتوى الكلوريدات	: صفر
الكثافة النوعية	: 1.14 ± 0.04 كجم / لتر
التعبئة	: 20 - 200 - 1000 لتر
الصلاحية	: عام من تاريخ الإنتاج عند درجة الحرارة العادية في عبواته المغلقة
التخزين	: في مكان جاف بعيدا عن التعرض لأشعة الشمس



ألترا أدد أف 730

إضافة للخرسانة فائقة الجوده لزيادة الإجهاد وتحسين قابلية التشغيل مع تأخير زمن الشك.



النشرة الفنية

معدل الإستخدام

2.5 : 0.8 لتر/ 100 كجم أسمنت.

يتم تحديد الكمية المطلوب إضافتها من المنتج بإجراء التجارب المعملية في محطة الخرسانةحـيث أن الجرعة تعتمد على عدة متغيرات منها نوعية الأســــمنت والركام ودرجة حـــــرارة الجو و مســـــافة نقـــــل الخرســـــانة وغيرها.

التوافق

- يتوافق مع جميع أنواع الأسمنت.









تعليمـات الأمـان

- يتم تنظيف أدوات التطبيق بعد إنتهاء الإستخدام مباشره قبل الجفاف والإ سيتم التنظيف ميكانيكا بعد الجفاف.
 - غير سامة طبقـا لقــواعد الصحــة والأمان السـائدة.
- يجب إرتداء الملابــس الواقــية المناسبـــة والقـــفازات وحـــماية العين ومعدات حـــماية الجهاز التنفســـى.
- عند التلامس مع الجلد يجب الغسل فورا بالماء والصابـون وإذا حـدث تلامس مع العين أو الأغشـية المخاطية يجب الشطف بالماء الدافىء وإستشارة الطبيب المختص.

لمزيد من التفاصيل ارجع إلى الداتا شيت باللغه الانجليزيه أو اتصل على الإداره الفنية.







المنطقة الصناعية - أبو رواش - الكيلو 26 طريق القاهرة الإسكندرية الصحراوي شارع عادل والي - قطعة رقم 91

جودة تستحق الثقة

Tel.:0100 931 8094 - 0100 044 9257

Email:sales@ultrachem-eg.com website: www.ultrachem-eg.com









المنطقة الصناعية -أبو رواش - الكيلو 26 طريق القاهرة الأسكندرية الصحراوي - شارع عادل والي Tel.: 0100 931 8094 - 0100 044 9257

Email:sales@ultrachem-eg.com website: www.ultrachem-eg.com



