



ULTRACHEM
For Construction Chemicals

Ultra Acry Mix

One-component, high-quality, ready mixed color decorative smooth finish facade render suitable for extreme weather conditions.

ألترا أكرى ميكس

تكسيه بأساس الاكريليك فائقة الجودة سابقة الخلط بألوان متعددة للواجهات الخارجية والداخلية.

Dry Mix



Made For You



Ultra Acry Mix

One-component, high-quality, ready mixed color decorative smooth finish facade render suitable for extreme weather conditions.

uses

Ultra Acry Mix is Acrylic based modified with polymer compound, high quality, extreme weather resistant, color stable, decorative facade render in paste form. internal and external applications over plastered substrates and fair face concrete. **Acry Mix** is ideal for is specially formulated to provide smooth finish when applied manually by trowel. Also, can be applied by spraying machine or Tyrolean to increase productivity and color uniformity. In this case will give rough finish surface. is similar to but formulated with micronized fillers that give an extra fine finished aspect.

Ultra Acry Mix Ideal for use in

- Facades and entrances of buildings and villas.
- Interior facades of buildings and ceilings.
- Facades of clubs, hospitals, and compound walls.
- Building facades in coastal areas.

Advantages

- Easy to apply and use, supplied ready for use directly on site.
- Raw materials are selected according to the highest quality control standards.
- Exact mixing ratios and homogeneity of the blend due to factory fully computerized production process.
- Available in wide range of uniform colors.
- Staple Color and unaffected by UV rays.
- Gives modern decorative finishing style.
- Excellent mixing and workability characteristics.
- High adhesion to all wet and dry internal and external surfaces.
- The simplicity of usage and application gives very high productivity rates.
- Maximum protection against salt formation or efflorescence compared with conventional decorative renders Therefore, it is suitable for coastal areas.
- Excellent bonding characteristics to plastered substrates and fair face concrete.
- Breathable, allows the substrate to breath without de-lamination.
- Excellent resistance to extreme weather conditions.

Description

Ultra Acry Mix One component paste ready to use, high-quality, ready mixed color decorative smooth finish facade render suitable for extreme weather conditions. **Ultra Acry Mix** is manufactured from carefully selected raw materials which include a blend of special high strength hydraulic binders, selected well graded fillers, and special additives to enhance workability, water retention, adhesion and color stability against U.V and resistant to extreme weather conditions.



Ultra Acry Mix

One-component, high-quality, ready mixed color decorative smooth finish facade render suitable for extreme weather conditions.

Properties

Color	: A wide range of colors.
Thickness	: 1 - 3 mm.
Density	: 1.9 ± 0.1 Kg/L.
Pot life	: 60 minutes depending on the air temperature.
Bond Strength	: > 3.0 N/mm ² .
Flexural Strength	: > 9.3 N/mm ² .
Compressive Strength	: > 18 N/mm ² .

instructions of use

Surface Preparation

Cement based walls and ceilings are the recommended substrates that can be covered with **Ultra Acry Mix**. Plastered substrates should be left to cure for at least 14 days prior to application of **Ultra Acry Mix**. Any problem in the substrate which may lead to water penetration must be rectified. All substrates should be in a good and strong condition. All substrates should also be clean and free from any loose particles, dust, oil, grease, curing agents., or paint. If the surface is dry and in hot weather, pre-wet prior to the application of **Ultra Acry Mix** without leaving excess water.

Application procedures

- Scaffolding must be fixed independently to allow for one go application.
- **Ultra Acry Mix** should be immediately applied on the surface to be applied, while the mortar is fresh and workable. In case of delay, do not add additional water. Remix till the mortar is workable again.
- Apply **Ultra Acry Mix** to the prepared surface either by conventional hand applied technique, Tyrolean or using spraying machine.
- It is recommended to apply a scratch coat of the same mixed **Ultra Acry Mix** prior to application of the final finish. The scratch coat should be left to set for 2 hours and pre-wetted prior to application of second coat.
- Structure the layer with plastic or wooden trowel before the surface dries in order to reach the required architectural finish.
- To achieve color consistency, apply **Ultra Acry Mix** in panels and complete it around the building.
- As natural raw materials are used for the production of **Ultra Acry Mix**, it is advisable to apply the entire facade at one time to ensure color uniformity as minor variations might be observed sometimes.



Ultra Acry Mix

One-component, high-quality, ready mixed color decorative smooth finish facade render suitable for extreme weather conditions.

Estimating

Supply

Ultra Acry Mix 25 kg pag

Coverage

8-10 m² pack of 25 kg
(the coverage rate may vary depending on the surface condition).

Storage

Shelf life

12 months from manufacturing date, in a dry, covered storage area.

Storage conditions

- store in dry conditions and in closed original packing.
- Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging.

Health and Safety

While using the product, gloves and goggles should be worn. Splashes to skin or eyes should be washed with clean water, in case of prolonged irritation, seek medical advice.



Quality You Can Trust

Aboraewash - Industrial Area
Cairo - Alex. Road Km. 26
Adel Wali St. Land No. 91

Tel.: 0100 931 8094 - 0100 044 9257

Email: sales@ultrachem-eg.com

website: www.ultrachem-eg.com

المنطقة الصناعية - أبو رواش - الكيلو 26
طريق القاهرة الإسكندرية الصحراوي
شارع عادل والي - قطعة رقم 91



ألترا أكري ميكس

تكسيه بأساس الاكريليك فائقة الجودة سابقة الخلط بألوان متعددة للواجهات الخارجية والداخلية.

وصف المنتج

عجينه جاهزه بأساس الأكريليك فائقة الجودة سابقة الخلط بألوان متعددة لتشطيب أسطح الحوائط الداخلية والخارجية ومناسبة لتشطيب حوائط البياض والأسقف والحوائط الخرسانية الملساء ذو مقاومة فائقة للعوامل الجوية المختلفة.

الإستعمالات

- واجهات المباني الخارجية في المناطق الساحلية.
- واجهات ومدخل العمارات والفيلات.
- الواجهات الداخلية للمباني والاسقف.
- واجهات النوادي والمستشفيات واسوار الكمبوندات.
- واجهات المباني الخارجية عموماً.

المميزات

- سهل التشغيل والإستخدام ولا يحتاج لمعدات خاصة لتطبيقه.
- ذو مقاومة فائقة للعوامل الجوية المختلفة وللظروف البيئية القاسية.
- يمكن إستخدامها يدوياً أو بالرش والتشطيب حسب الإختيار.
- تعطى شكل جمالي بألوانها الزاهية ولها مقاومة لعوامل الجو المختلف.

البيانات الفنية

(عند 25 درجة مئوية)

اللون	:	عدد كبير جدا من الألوان حسب الطلب
الأساس	:	راتنجات الاكريليك و رمل سيليكاً نقي مدرج وألوان وإضافات
كثافة البودرة	:	1.9 ± 0.1 كجم / لتر تقريبا
مدة التشغيل	:	60 دقيقة بعد الخلط حسب درجة حرارة الجو
التعبئة	:	شكاثر زنة 25 كجم
الصلاحية	:	12 شهر من تاريخ الإنتاج في عبواته المغلقة
التخزين	:	في مكان جاف بعيداً عن التعرض لأشعة الشمس

معدل الإستخدام

- 1.3 - 1.75 كجم / لسمك 1 مم للنوع الناعم.
- 2 - 3 كجم / للنوع الخشن.
- معدلات التغطية قد تختلف تبعاً لدرجة خشونة المنتج وتبعاً لحالة السطح.



ألترا أكري ميكس

تكسيه بأساس الاكربليك فائقة الجودة سابقة الخلط بألوان متعددة للواجهات الخارجية والداخلية.

التطبيق والإستخدام إعداد السطح

- الجدران والأسقف الأسمنتية هي الركائز الموصى بها والتي يمكن تغطيتها باستخدام **ألترا أكري ميكس**.
- يجب ترك الركائز لتجف لمدة 14 يوماً على الأقل قبل تطبيق **ألترا أكري ميكس**.
- يجب تصحيح أي مشكلة في الركيزة قد تؤدي إلى إختراق الماء، كذلك يجب تصحيح جميع الركائز أن تكون في حالة جيدة وقوية.
- يجب أن تكون كل الاسطح نظيفه وخاليه من أي أتربة أو زيوت أو شحوم.
- تبلل الأسطح بالماء قبل التشغيل.

التطبيق

- يتم تقليب الشيكاره تقليب هين للحصول على قوام متسق لمدته دقيقتان ثم تترك لمدة 3 دقائق بعد الخلط قبل الإستخدام.
- يتم فرد المادة على السطح بإستخدام البروة بسمك 1 - 3 مم , ثم يتم تشطبيها بفرطاسه جيده ومناسبة.



تعليمات الأمان

- يتم تنظيف أدوات التطبيق بعد إنتهاء الإستخدام مباشرة قبل الجفاف والإ سيتم التنظيف ميكانيكا بعد الجفاف.
- غير سامة طبقاً لقواعد الصحة والأمان السائدة.
- يجب إرتداء الملابس الواقية المناسبة والقفازات وحماية العين ومعدات حماية الجهاز التنفسي.
- عند التلامس مع الجلد يجب الغسل فوراً بالماء والصابون وإذا حدث تلامس مع العين أو الأغشية المخاطية يجب الشطف بالماء الدافىء وإستشارة الطبيب المختص.

لمزيد من التفاصيل ارجع إلى الداتا شيت باللغة الانجليزية أو اتصل على الإدارة الفنية.

جودة تستحق الثقة



Aboraewash - Industrial Area
Cairo - Alex. Road Km. 26
Adel Wali St. Land No. 91

Tel.: 0100 931 8094 - 0100 044 9257
Email: sales@ultrachem-eg.com
website: www.ultrachem-eg.com

المنطقة الصناعية - أبو رواش - الكيلو 26
طريق القاهرة الإسكندرية الصحراوي
شارع عادل والي - قطعة رقم 91



ULTRACHEM

For Construction Chemicals



المنطقة الصناعية - أبو رواش - الكيلو 26
طريق القاهرة الأسكندرية الصحراوي - شارع عادل والي

Tel.: 0100 931 8094- 0100 044 9257

Email: sales@ultrachem-eg.com

website: www.ultrachem-eg.com

